

# Alsitherm EPS 034 Quattro

Polystyrene insulation boards for alsecco facade systems



## AREAS OF APPLICATION

Artikel	Description
Alsitherm EPS 034 Quattro	Insulation boards with butt edges for fixing by means of bonding or bonding and anchoring with increased thermal insulation for alsecco facade systems.

## PRODUCT PROPERTIES

- Area of application according to DIN 4108-10: WAP
- EPS - DIN EN 13163 - T1 - L2 - W2 - S2 - P3 - DS(70,-)2 - DS(N)2
- Dimensionally stable
- Quality controlled according to DIN EN 13163 and the quality guidelines for facade insulation boards of the IVH (Industrial Association for Rigid Foam) and the ETICS Trade Association.
- HBCD free, CFC and HCFC free
- Flame-resistant according to DIN 4102

## TECHNICAL DATA

Fire behavior	B1 according to DIN 4102 E according to DIN EN 13501
Thermal conductivity $\lambda$	Calculation value 0,034 W/(mK) in accordance with DIN 4108-4 Rated value $\lambda_D$ : 0,033 W/(mK)

Dimensions

Type	Dimension
Blunt	100 x 50 cm
Step rabbet	98 x 48 cm
Tongue and groove	99 x 49 cm

Water vapour diffusion resistance  $\mu$  20/40 according to DIN EN 13163

Water absorption < 1 kg/m<sup>2</sup> according to EN 1609

## APPLICATION INSTRUCTIONS

Substrate pre-treatment Pretreat substrates according to the application instructions for the adhesive.

Application

### Fixing in bonded as well as bonded and anchored systems:

Depending on the substrate, bond with respective system adhesive mortar according to the bead-spot method.

Bonding surface percentage of at least 40%. Ensure a minimum bonding of 60% for adhesive applications on walls.

Adhesive application using buttering-floating method is possible for very level substrates.

Butt insulation boards together. Do not apply any adhesive to butt or bed joints.

Installation using stretcher bond formation offset by at least 10 cm. Interlock insulation material on building corners.

Butt joints on insulation boards may not be above the connection zones of different components (e.g. ring beams, roller shutter boxes, element joints). Here, the insulation material should bridge a space of at least 10 cm and be supported on both sides by means of a reliable bond.

Seal open joints between the insulation boards with filling foam B1 for joint widths < 0.5 cm, seal larger joints using insulating strips.

For substrates suitable for bonding, provide additional structural anchoring if necessary.

Anchoring of substrates unsuitable for bonding according to the general approval by building authorities for ETICS.

Observe the application instructions for the adhesive when using Speed-Fix adhesive foam.

### Follow-up work

Sand down unevenness and remove the accumulated dust (see "Installation ETICS" brochure).

Consumption

Type	Consumption ca.
Blunt	1,00 m <sup>2</sup> /m <sup>2</sup>
Step rabbet	1,06 m <sup>2</sup> /m <sup>2</sup>
Tongue + groove	1,04 m <sup>2</sup> /m <sup>2</sup>

Informations

Unrendered insulation boards on the facade must be protected against moisture and coated with reinforced undercoat render as soon as possible.

Do not install damaged insulation boards.

The existing expansion joints on the building must be included in the external thermal insulation cladding system.



You can find possible fire protection measures for greater thicknesses ( $100 \text{ mm} < d \leq 300 \text{ mm}$ ) to maintain flame resistance in the respective approval or the explanations: Technical System Information 6 of the Fachverband Wärmedämm-Verbundsystem e.V.

## STORAGE

Dry, protected against moisture and sunlight.

## PACKAGING INFORMATION

Colour Grey-white speckled

## OTHER INFORMATION

Information on safety	The information provided in the current safety data sheet applies.
Transportation	Not a hazardous material
Waste code	17 06 04(class II waste disposal, household and construction waste disposal)

**alsecco GmbH**  
Kupferstraße 50  
D-36208 Wildeck  
Phone 03 69 22 / 88-0  
Fax 03 69 22 / 88-330  
Internet: [www.alsecco.de](http://www.alsecco.de)

The above information is based on many years of experience and tests and is provided by us to the best of our knowledge. Such information applies in addition to our application guidelines. However, we cannot accept any responsibility for the correctness of our recommendations on account of wide variety of substrates and of on-site conditions and applications which are outside our control. Any recommendations provided by our employees and deviating from these documents must be given in writing. We reserve right to make any changes on account of technical progress or building regulations. Your technical advisor will be pleased to provide the relevant product data sheets.

