

Kellerdeckendämmplatte Quattro

Polystyrene insulation boards for interior applications



AREAS OF APPLICATION

Ceiling insulation board for systems with adhesive fixing, and with adhesive and mechanical fixing, for insulating interior ceilings.

PRODUCT PROPERTIES

- Area of application in accordance with DIN 4108-10: DI
- EPS insulation board in accordance with DIN EN 13163 - L3-W3-T2-S5-P10-BS50-DS(N)5-DS(70,-)3
- Dimensionally stable
- HBCD free, CFC and HCFC free
- Edges: Rabbet and exposed face with bevel (7 x 7 mm)

TECHNICAL DATA

Fire behavior	E according to DIN EN 13501-1
Thermal conductivity λ	Calculation value 0,035 W/(mK) in accordance with DIN 4108-4 Rated value λ_D : 0,034 W/(mK)
Dimensions	980 mm x 480 mm
Thickness	40 - 120 mm
Accessories	Ceiling insulation screw DDS-Z Ceiling insulation disc DDT
Water vapour diffusion resistance μ	20/70 according to DIN EN 13163
Density	approx. 22 kg/m ³

APPLICATION INSTRUCTIONS

Substrate pre-treatment	Pretreat substrates according to the application instructions for the adhesive.
Application	<p>Apply adhesive using the spot-and-bead method. At least a 40 % bond must be achieved. If the substrate is very smooth, the adhesive may be applied using the ridged-bed method.</p> <p>Only fast-setting types of adhesive, such as Armatop MP or Dämmkleber MK (Thermastick MK) are suitable for fixing insulation boards to the ceiling.</p> <p>The insulation boards are butted close together.</p> <p>The vertical and horizontal joints of the boards must be kept free of adhesive.</p> <p>The boards may subsequently be coated.</p>

STORAGE

Dry, protected against moisture.

PACKAGING INFORMATION

Colour	White
Packaging unit	Please also refer to the current product range

OTHER INFORMATION

Transportation	Not a hazardous material
Waste code	17 06 04(class II waste disposal, household and construction waste disposal)

alsecco GmbH
Kupferstraße 50
D-36208 Wildeck
Phone 03 69 22 / 88-0
Fax 03 69 22 / 88-330
Internet: www.alsecco.de

The above information is based on many years of experience and tests and is provided by us to the best of our knowledge. Such information applies in addition to our application guidelines. However, we cannot accept any responsibility for the correctness of our recommendations on account of wide variety of substrates and of on-site conditions and applications which are outside our control. Any recommendations provided by our employees and deviating from these documents must be given in writing. We reserve right to make any changes on account of technical progress or building regulations. Your technical advisor will be pleased to provide the relevant product data sheets.

