Klefu

Adhesive and joint filler for aerated concrete elements

AREAS OF APPLICATION

Bonding and pointing of horizontal joints on outdoor aerated concrete elements.

PRODUCT PROPERTIES

- Good crack bridging
- Low scale of shrinkage
- Can be painted with all paint
- Suitable for overhead work
- Force-locked bond due to special additives
- High filling capacity due to quartz sand additive

TECHNICAL DATA

Binder base	Acrylic dispersion
Specific gravity	approx. 1,8 g/cm³

APPLICATION INSTRUCTIONS

Substrate pre-treatment: All substrates must be dry, clean and free of any residue, which can reduce adhesiveness.

Application

Area of application	
Bonding	Apply one strand ≥ 10 mm diameter per 10 cm thickness of the aerated concrete element.
Pointing	Insert in horizontal bevelled bed joint and swipe smooth with a moist brush. Adapt the brush size to the width of the joint.

alsecco
FASSADENKOMPETENZ

Consumption

Area of application	
Bonding	approx. 200 g/m Strand
Pointing	approx. 150 g/m Strand

Determine the precise material requirements on the respective object.

Information about the weather: Temperatures cannot fall below +3 °C during application and drying.

Drying time: approx. 4 - 24 hours
Dependent on temperature and relative humidity.

Cleaning of tools: In a fresh state with water.

STORAGE

Shelf life in original sealed packaging of at least 1 year when kept cool and protected against frost.

PACKAGING INFORMATION

Colour: Natural white

Packaging unit: Plastic tubular bag approx. 3 kg net

OTHER INFORMATION

Information on safety: The information provided in the current safety data sheet applies.

Transportation: Not a hazardous material

Giscode: M-DF02F latex paints, active substances

alsecco GmbH
Kupferstraße 50
D-36208 Wildeck
Phone 03 69 22 / 88-0
Fax 03 69 22 / 88-330
Internet: www.alsecco.de

The above information is based on many years of experience and tests and is provided by us to the best of our knowledge. Such information applies in addition to our application guidelines. However, we cannot accept any responsibility for the correctness of our recommendations on account of wide variety of substrates and of on-site conditions and applications which are outside our control. Any recommendations provided by our employees and deviating from these documents must be given in writing. We reserve right to make any changes on account of technical progress or building regulations. Your technical advisor will be pleased to provide the relevant product data sheets.

alsecco
FASSADENKOMPETENZ