

# Siliconharzputz R

Silicon resin render with grooved finish



## AREAS OF APPLICATION

Paste-like render finish according to DIN EN 15824 for mineral and organic render systems on exterior walls and ceilings.

Can be used in connection with the alsecco facade systems, in particular with System Alprotect Quattro.

## PRODUCT PROPERTIES

- Extremely easy to apply
- High mechanical load capacity
- High colour stability
- High level of protection against microbial infestation
- With encapsulated film protection
- Water-repellent
- Water-vapour permeable
- A2-s1, d0 (fireproof) according to DIN EN 13501

## TECHNICAL DATA

Indicated fixed values represent average values, which can slightly vary from delivery to delivery due to the application of natural raw materials.

Binder base	Silicone resin emulsion Acrylic resin dispersion
Specific gravity	approx. 1,75 g/cm <sup>3</sup>
Water permeability	w: approx. 0,13 kg/(m <sup>2</sup> h <sup>1/2</sup> ) according to DIN EN 1062 Class W <sub>2</sub> according to DIN EN 1062
Fire behavior	A2-s1, d0 according to DIN EN 13501
Diffusion-equivalent air-layer thickness (3,0 mm)	s <sub>d</sub> : approx. 0,18 m according to DIN EN ISO 7783 Class V <sub>2</sub> according to DIN EN 1062

**APPLICATION INSTRUCTIONS**

Preparation	Mask window sills and attachment parts. First, render the reveals.
Substrate pre-treatment	All substrates must be stable, level, clean, dry and free of any residue, which can reduce adhesiveness. If applicable, the stability of substrates can be ensured by applying suitable primers. We recommend a priming coat with Primer SC, to improve workability before applying the decorative render.
Mixing	Ready to use. Can be adjusted to a workable consistency with a max. of 2 % water.
Application	Apply in grain size with a rustproof steel trowel and after a brief period, spread with a plastic trowel using circular, vertical or horizontal motions. Complete contiguous surfaces without any stopping (to avoid seams in the textured coating). Divide large facades into sections, apply continuously wet-on-wet and texture. For light reflectance values below 20, the render must be coated with at least two coats of a suitable alsecco paint or varnish system after drying, preferably Alsicolor Carbon or Alsicolor Sc.
Consumption	Grain size 1,5 mm approx. 2,5 kg/m <sup>2</sup> Grain size 2,0 mm approx. 3,2 kg/m <sup>2</sup> Grain size 3,0 mm approx. 4,2 kg/m <sup>2</sup> Grain size 4,0 mm approx. 4,7 kg/m <sup>2</sup> Determine the precise material requirements by means of a trial coating on the object.
Information about the weather	Temperatures below 5 °C may not arise during application and drying. Do not apply in direct sunlight. In the case of wind, please observe shorter setting times.
Drying time	approx. 1 - 2 days Dependent on temperature, layer thickness and relative humidity.
Cleaning of tools	In a fresh state with water.
Application by machine	Please request special information regarding machine processing.

**STORAGE**

Shelf life in original sealed packaging of at least 1 year when kept cool and protected against frost.

**PACKAGING INFORMATION**

Colour	White and pigmented. Use material from one batch number for pigmented materials or contiguous surfaces.
Packaging unit	PP bucket approx. 25 kg net

**OTHER INFORMATION**

This products provides a high level of protection against microbial infestation, a permanent exclusion of infestation cannot be guaranteed.

Information on safety	The information provided in the current safety data sheet applies.
Transportation	Not a hazardous material
Giscode	M-SF01 silicone resin paints, water soluble, active substances

**alsecco GmbH**  
Kupferstraße 50  
D-36208 Wildeck  
Phone 03 69 22 / 88-0  
Fax 03 69 22 / 88-330  
Internet: [www.alsecco.de](http://www.alsecco.de)

The above information is based on many years of experience and tests and is provided by us to the best of our knowledge. Such information applies in addition to our application guidelines. However, we cannot accept any responsibility for the correctness of our recommendations on account of wide variety of substrates and of on-site conditions and applications which are outside our control. Any recommendations provided by our employees and deviating from these documents must be given in writing. We reserve right to make any changes on account of technical progress or building regulations. Your technical advisor will be pleased to provide the relevant product data sheets.



FASSADENKOMPETENZ