

# Fugenbrückenband

Reinforcement of joints between structural panels and anti-crack reinforcement in the Hydroelast 2000 system.



## AREAS OF APPLICATION

Reinforcement layers for joints between components.  
Crack reinforcement in fillers and coatings.

## PRODUCT PROPERTIES

- Alkali-resistant
- Non-slip

## TECHNICAL DATA

Weight per unit area	approx. 85 g/m <sup>2</sup>
Mesh size	approx. 1,5 x 1,5 mm <sup>2</sup>
Tensile force	lengthwise: approx. 850 N/5 cm crosswise: approx. 850 N/5 cm
Elongation	lengthwise: approx. 3 % crosswise: approx. 3 %

## APPLICATION INSTRUCTIONS

Application	Insert mesh into open reinforcing compound and rework in the second step.
Consumption	approx. 1,1 m <sup>2</sup> /m <sup>2</sup>

**PACKAGING INFORMATION**

Colour	Natural white
Packaging unit	Rolls 10 cm wide : 50 m long

**alsecco GmbH**  
Kupferstraße 50  
D-36208 Wildeck  
Phone 03 69 22 / 88-0  
Fax 03 69 22 / 88-330  
Internet: [www.alsecco.de](http://www.alsecco.de)

The above information is based on many years of experience and tests and is provided by us to the best of our knowledge. Such information applies in addition to our application guidelines. However, we cannot accept any responsibility for the correctness of our recommendations on account of wide variety of substrates and of on-site conditions and applications which are outside our control. Any recommendations provided by our employees and deviating from these documents must be given in writing. We reserve right to make any changes on account of technical progress or building regulations. Your technical advisor will be pleased to provide the relevant product data sheets.

