

Armierungsgewebe PB

Reinforcement of aerated concrete sealants



AREAS OF APPLICATION

Reinforcement layers on aerated concrete elements for indoor and outdoor use.

PRODUCT PROPERTIES

- Alkali-resistant
- Non-slip

TECHNICAL DATA

Weight per unit area	approx. 58 g/m ²
Mesh size	approx. 2,2 x 2,3 mm ²
Tensile force	lengthwise: approx. 850 N / 5 cm crosswise: approx. 700 N / 5 cm
Elongation	lengthwise: approx. 4,0 % crosswise: approx. 4,0 %

APPLICATION INSTRUCTIONS

Application	Insert mesh into open reinforcing compound. For fillers, overlapping by 10 cm in the joint area. Butt up for coating. Then, rework the mesh using the same material.
Consumption	approx. 1,1 m ² /m ² Depending on whether worked as a filler (overlapping 10cm) or a coating (butt).

PACKAGING INFORMATION

Colour	White
Packaging unit	Rolls 60 cm wide : 50 m long

alsecco GmbH
Kupferstraße 50
D-36208 Wildeck
Phone 03 69 22 / 88-0
Fax 03 69 22 / 88-330
Internet: www.alsecco.de

The above information is based on many years of experience and tests and is provided by us to the best of our knowledge. Such information applies in addition to our application guidelines. However, we cannot accept any responsibility for the correctness of our recommendations on account of wide variety of substrates and of on-site conditions and applications which are outside our control. Any recommendations provided by our employees and deviating from these documents must be given in writing. We reserve right to make any changes on account of technical progress or building regulations. Your technical advisor will be pleased to provide the relevant product data sheets.

